



Gum Rosin X, WW, WG

Technical Data Sheet
midhills

Latest Updated 05/08/2019

REMARK

The above information is believed to be accurate and presents the best explanation currently available to us. We assume no liability resulting from above content. The technical standards are formulated and revised by customers requirements. if there are any changes the latest specification will be executed and confirmed in the contract.

midhills

Gum Rosin

CAS 8050-09-7 EINECS 232-475-7

- Main material of modified resins.
- Used for paper making industry.
- A film forming material for fertilizers release control.

- Galvanised iron drums 200 Kg net each.
- Accept OEM order.

Packing Available

- Iron Drum, 225kg net each.
- Paper Bag, 25kg net each.
- Iron Tins 17 Kg net each.
- Iron drums 200 kg net each.
- Iron drums 100 kg net each.
- Custom packing also available.

Storage Conditions

- Avoid contact with light.
- Keep separated from incompatible substances.
- Store and handle in accordance with all current regulations and standards.
- Store in a cool, dry place.
- Store in a tightly closed container.

Item	X	WW	WG
Colour, Fe-Co Scale	Slight Yellow	Light Yellow	Deep Yellow
Softening Point, R&B, °C	75 min	76 min	75 min
Acid Value, mg KOH/g	165 min	166 min	165min
Ash, %	0.03 max	0.03 max	0.04 max
Insoluble in Alcohol, %	0.03 max	0.03 max	0.03 max
Unsaponifiable Matter, %	5 max	5 max	5 max